

Circular Economy in Food Industry Waste Management (BIVALIA Workshop2 - 2026)

Editors: Elena Díaz Nieto; Francisco Heras Muñoz; Juan Antonio Melero Hernández; Manuel Gertrudix

Madrid, BIVALIA, UAM-URJC, 2026

DOI: 10.5281/zenodo.22206833 · CC BY 4.0

Full volume: <https://books.ciberimaginario.cloud/libro/bivalia-w2-2026>

OFFPRINT · PP. 6–7

Valorization of food waste into carbon-based materials and bio-based chemicals and fuels

Lucília S. Ribeiro¹, Rafael G. Morais¹, Rui S. Ribeiro¹, José J. M. Órfão¹, M. Fernando R. Pereira^{1*}

1: LSRE–LCM, ALiCE, Faculty of Engineering, University of Porto, Rua Dr. Roberto Frias, 4200-465 Porto, Portugal

Integrated catalytic process; Waste-derived carbons; Carbohydrate valorization; Renewable platform molecules; Hydrogenative upgrading; C–C coupling; Sustainable aviation fuels

HOW TO CITE THIS CONTRIBUTION

Lucília S. Ribeiro, Rafael G. Morais, Rui S. Ribeiro, José J. M. Órfão, M. Fernando R. Pereira. (2026). Valorization of food waste into carbon-based materials and bio-based chemicals and fuels. In: Díaz Nieto, E., Heras Muñoz, F., Melero Hernández, J. A., Gertrudix, M. (Eds.), Circular Economy in Food Industry Waste Management (BIVALIA Workshop2 - 2026), pp. 6–7. BIVALIA, UAM-URJC. <https://doi.org/10.5281/zenodo.22206833>

Invited Speakers #1

Valorization of food waste into carbon-based materials and bio-based chemicals and fuels

Lucília S. Ribeiro¹, Rafael G. Morais¹, Rui S. Ribeiro¹, José J. M. Órfão¹, M. Fernando R. Pereira^{1*}

¹ LSRE-LCM, ALiCE, Faculty of Engineering, University of Porto, Rua Dr. Roberto Frias, 4200-465 Porto, Portugal

*Correspondence: fpereira@fe.up.pt

Keywords: Integrated catalytic process; Waste-derived carbons; Carbohydrate valorization; Renewable platform molecules; Hydrogenative upgrading; C–C coupling; Sustainable aviation fuels

Food waste is an abundant renewable carbon resource with considerable potential for the production of functional materials, platform chemicals, and sustainable fuels. This work presents an integrated valorization strategy in which food residues are used both as feedstocks for catalytic conversion and as precursors for carbon materials and catalysts.

Glucose-derived and food waste-derived catalytic materials were developed and applied to the conversion of cellulose and carbohydrate-rich food residues into ethylene glycol (EG), demonstrating the feasibility of coupling renewable feedstocks with carbon-based catalytic materials. Within this integrated framework, food residues were also converted into carbonaceous materials through hydrothermal carbonization, followed by carbonization/activation treatment, with the resulting materials applied to the production of biomass-derived value-added chemicals, including EG and furfural.

Low-cost Ni–W catalysts supported on glucose-derived carbons were developed for the one-pot conversion of cellulose into EG, achieving complete cellulose conversion and EG yields of 60–62 % [1-2]. The optimized glucose-derived catalysts were also applied to real waste, producing EG yields of around 40 % from cellulosic urban wastes and up to 21 % through the direct conversion of banana peel, orange peel, and spent coffee grounds [1]. To further integrate waste into catalyst synthesis, orange- and banana-peel-derived carbons were used as Ni–W catalyst supports, yielding 34.7 and 44.3 % EG from cellulose, respectively [3]. Additionally, preliminary results obtained with activated carbon derived from orange peel showed a highly developed porous structure and effective catalytic performance in xylose dehydration, reaching 98 % conversion and a furfural yield of 30.4 %.

The approach further integrates the production of furfural and levulinic acid from carbohydrate-rich feedstocks with their subsequent upgrading into sustainable aviation fuel precursors. These oxygenated platform molecules then undergo carbon–carbon coupling reactions, followed by hydrodeoxygenation, to produce hydrocarbons within the carbon-number range relevant for aviation fuels (C₈–C₁₆).

Overall, this strategy combines waste-derived material synthesis, carbohydrate conversion, and catalytic upgrading within a unified framework, demonstrating the versatility of food waste as both a source of catalytic materials and a renewable feedstock for chemicals and fuels.

Acknowledgements

This work was financially supported by Fundação para a Ciência e a Tecnologia, I.P./MECI through national funds: LSRE-LCM, UID/50020/2025 (<https://doi.org/10.54499/UID/50020/2025>); and ALiCE, LA/P/0045/2020 (<https://doi.org/10.54499/LA/P/0045/2020>). This work was also supported by national funds through the FCT/MECI, under the project Waste2Jet - Food Waste Catalytic Valorisation into Eco-Friendly Aviation Fuels: A Pathway for Sustainable Air Transportation with reference 2024.14180.PEX and with DOI <https://doi.org/10.54499/2024.14180.PEX>. In addition, this work was supported by Calouste Gulbenkian Foundation, under research project GREENSHIP_E – Electrification of Ships Using Green Fuels and Advanced Technologies. RSR acknowledges the FCT funding under Stimulus of Scientific Employment, Individual Support Call – 5th Edition, 2022.04079.CEECIND/CP1733/CT0006 (DOI: [10.54499/2022.04079.CEECIND/CP1733/CT0006](https://doi.org/10.54499/2022.04079.CEECIND/CP1733/CT0006)).

References

1. L. S. Ribeiro, R. G. Morais, J. J. M. Órfão, and M. F. R. Pereira, "Unlocking the value of food waste: sustainable production of ethylene glycol over low-cost Ni–W catalysts supported on glucose-derived carbons," *Sustainable Energy and Fuels*, vol. 8, no. 19, pp. 4588-4601, 2024. <https://doi.org/10.1039/d4se00823e>
2. R. G. Morais, L. S. Ribeiro, J. J. M. Órfão, and M. F. R. Pereira, "Low-Cost Ni-W Catalysts Supported on Glucose/Carbon Nanotube Hybrid Carbons for Sustainable Ethylene Glycol Synthesis," *Molecules*, vol. 29, no. 16, p. 3692, 2024. <https://doi.org/10.3390/molecules29163962>
3. L. S. Ribeiro, R. G. Morais, A. C. Damas, J. J. M. Órfão, and M. F. R. Pereira, "Synthesis of Ni-W catalysts supported on fruit peel waste-derived carbons for the efficient ethylene glycol production from cellulose," *Cellulose*, vol. 32, pp. 3633-3649, 2025. <https://doi.org/10.1007/s10570-025-06464-4>